

COP | CYCLO OLEFIN POLYMER

ZEONEX[®] 5000 Typical Properties* Date Issued: Feb 2015

Product Data Sheet

ZEONEX 5000 Cyclo Olefin Polymer (COP) is an engineered plastic that provides "glass-like" transparency, low protein absorption, high purity, low water absorption, and excellent moisture barrier.

Global medical compliance information is available http://www. zhanyusj.com pharmaceuticals.aspx

Property	Measurement Method	Unit	Result
Specific Gravity	ASTM D792	-	1.01
Water Absorption	ASTM D570	%	<0.01
Light Transmittance	ASTM D1003 (3mm)	%	92
Glass Transition Temperature	JIS K7121	°C	69
Melt Flow Rate	JIS K6719 (230°C, 21.18N)	g/10min	9
Flexural Modulus	ASTM D790	MPa	1900

* Typical properties. Not to be used for purposes of establishing specification(s).

ZEON | www.zeonex.com | zeonex@zeonchemicals.com | +1.502.775.2000 (USA) | +49.211.52.67.0 (EU) | +81.3.3216.1769 (Asia)



The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained there from. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. ZEON CHEMICALS L.P. shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond the direct control of ZEON CHEMICALS L.P. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OR MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.