

Technical Data Sheet / 技術資料表

2024.03.31 REVISED

GLOBALPRENE 7533				
Styrene-Ethylene/Butylene block copolymer 苯乙烯-乙烯/丁烯嵌段共聚物				
Features 特性 :		Typical Application 一般應用 :		
Linear block copolymer	線狀嵌段共聚物	Plastic modification	塑膠改質	
High compression set	高壓縮永久變形	Compounding for modification	混煉改質	
High mechanical strength	高機械強度	Automotive	車用	
Good compatibility with plastics	與塑膠有好的相容性	Adhesive	膠黏劑	
Typical Properties :	Test Method	Unit	Value	Range
一般性質	測試方法	單位	數值	範圍
SM Content 苯乙烯含量	ASTM D5775	%	31.5	30 ~ 33
Specific Gravity 比重	ASTM D792	-	0.91	≥ 0.91
Volatile Matter 揮發份	ASTM D5668	%	0.2	≤ 0.5
Ash Content 灰份	ASTM D5667	%	0.6	≤ 1.0
5wt% / 25°C Toluene Viscosity 5wt% / 25°C 甲苯黏度	ASTM D2196	cP	400	250 ~ 550

Note : SM content is measured on polymer before hydrogenation. 苯乙烯含量為氫化前測量值

Packing 包裝: 13kg PE bag

All ingredients in the products are in compliance with the following chemical inventories:

United States: Toxics Substances Control Act Inventory (TSCA)

Canada: Domestic Substances List (DSL)

Europe: EINECS/ELINCS replaced by REACH

Australia: Australian Inventory of Chemical Substances (AICS)

New Zealand: New Zealand Inventory of Chemicals (NZIoC)

Korea: Korean Existing Chemicals List (KECL)

Japan: Japanese Inventory of Existing and New Chemical Substances (ENCS)

The Philippines: Philippines Inventory of Chemicals and Chemical Substances (PICCS)

China: Inventory of Existing Chemical Substances Manufactured or Imported in China (IECSC)

Taiwan: Existing Chemical Substances Inventory (ECSI)

免責聲明 Disclaimer

以上所列之各項資料為實驗參考值，唯因使用時加工條件及環境之不同，而產生之差異非本公司所能保證與控制。本公司不對從上述資訊得出的任何發現、推薦或建議做擔保或保證，亦不承擔任何法律義務或責任。

The values quoted here are typical of the grade, however, it is important to recognize that some variation around these values is to be expected as a result of uncertainties associated with measurement of the specific property and due to the normal variations encountered during the manufacturing process. LCY does not guarantee any findings, recommendations, or suggestions derived from the above information. LCY disclaims any and all liability for the damages arising from the use of this information.

商務服務處

臺灣 臺北市松山區八德路四段 85 號 3 樓

Tel : +886-2-27631611

Sales Services

3F., No.85, Sec. 4, Bade Rd., Songshan Dist., Taipei City 105, Taiwan

Fax : +886-2-27482661

惠州李長榮橡膠有限公司

中國 廣東省惠州市大亞灣經濟技術開發區石化區石化大道中 299 號 No.299

Tel : +86-752-5599000

Shihua Dadaozhong, Dayawan Economic & Technological Development Zone, Huizhou, Guangdong, 516082, P.R.C.

Fax : +86-752-5599002